



TECHNICAL DATA SHEET

STEVENS URETHANE AG4950

Stevens Urethane AG4950 is an aliphatic polyurethane with low modulus specifically formulated to be used as an adhesive interlayer without the need for a glass surface primer.

Stevens Urethane AG4950 contains a UV additive package to protect itself and materials below it from harmful UV radiation.

Physical Properties	Test Methods	Typical Value
Tensile strength at 100%, psi	ASTM D412*	340
Tensile strength at 200%, psi	ASTM D412*	475
Tensile strength at 300%, psi	ASTM D412*	650
Tensile strength at Break, psi	ASTM D412*	3500
Elongation at Break, %	ASTM D412*	770
Tear Strength, pli	ASTM D624	TBD
Specific Gravity	ASTM D792	1.06
DSC mid Point, T _g °C	N/A	-60
TMA Peak, °C	N/A	92
TMA Range, °C	N/A	60 – 140
Coefficient of Thermal Expansion L/Lo °C	N/A	~0.0003

* - Note: ASTM D412 Die C is used with a grip separation rate of 20 in/min

Optical Properties**	Test Methods	Typical Value
Haze, %	ASTM D1003	0.3
Transmission, %	ASTM D1003	90
Yellowness Index	ASTM D1925	<1
Refractive Index	ASTM D542	1.486

**Film tested between two pieces of 1/8” glass
Film Thickness for Optical Properties – 0.050”

Created
February 2007



412 Main Street, Easthampton, Massachusetts 01027-1918
Tel: 413-779-1200 Fax: 413-779-1259
Internet: www.stevensurethane.com

